

Specification	Details
Product name	S4152I Aftermarket Automotive
Date	31/01/2022
Application	Automotive, furniture, aviation, boating
Material	Grain leather, chrome tanned
Tear strength (ISO 3377-1)	≥ 20 N
Tensile strength (ISO 3376)	≥ 130 N
Colour fastness to rubbing — dry (ISO 11640)	≥ 4 (1,500 cycles)
Colour fastness to rubbing — wet (ISO 11640)	≥ 4 (300 cycles)
Colour fastness to perspiration (ISO 11640 & 11641)	≥ 4 (100 cycles)
Flex resistance (ISO 5402)	50,000 cycles, no damage
Adhesion of finish (ISO 11644)	≥ 4 N/cm
Colour fastness to artificial light (ISO 105-B02)	≥ 4 (16,000 kJ/m²)
Artificial ageing	4 h @ 70°C, ≥ 4
Flammability (FMVSS 302)	< 100 mm/min
Cigarette & match resistance (BS 5852:1979)	Pass
Notes	Values may vary depending on color, thickness, and customer requirements.