

Specification	Details
Product name	VESUVIO ARREDO premium nappa
Application	Upholstery, contract
Origin	Bovine (Bos taurus) — North America
Average size	48–54 PQ (approx. 4.8 – 5.4 m²)
Thickness	0.9 – 1.1 mm
Tanning type	Chrome tanning
Finishing	Semianiline, no embossing
Appearance	Soft hand, conform to master sample
Thickness test (ISO 2589)	0.9 – 1.1 mm
Colour fastness to rubbing (ISO 11640)	Dry: 500 cycles ≥ 4 Wet: 150 cycles ≥ 4 Alkaline perspiration: 50 cycles ≥ 4
Flexing resistance (ISO 5402-1)	30,000 cycles, no cracks
Tear strength (ISO 3377-1)	Not specified here
Colour fastness to water spotting (ISO 15700)	No halo, no blistering
Adhesion of finish (ISO 11644)	Dry ≥ 3 N/cm
Colour fastness to artificial light (ISO 105 B02:2015)	≥ 4 (after 72 h)
Chemical compliance	REACH regulation CE 1907/2006 compliant; heavy metals (Cd ≤ 1000 mg/kg, Pb ≤ 100 mg/kg); phthalates ≤ 50 mg/kg each
Storage & processing	10–12% humidity, max 80°C; avoid solvents; store dry at 15–25°C without heavy loads; test prototypes before production.
Finished product care	Store dry at room temperature; test cleaning products first; clean stains promptly by dabbing; air-dry and polish with soft cloth.
Notes	Values are average from standard production; specs may change without notice.