

Specification	Details
Product name	TANGO NG ARREDO BOV.INT.
Issued on	26/06/2025
Application	Upholstery
Origin	Bovine (Bos taurus) — South America
Average size	4.6 – 5.1 m²
Thickness	0.9 – 1.1 mm
Tanning type	Chrome tanning
Finishing	Pigmented, embossed
Elasticity, fullness, flexibility	Conform to master sample
Thickness test (ISO 2589)	0.9 – 1.1 mm
Color fastness to rubbing (ISO 11640)	Dry: 500 cycles ≥ 4; no damage Wet: 250 cycles ≥ 3/4; no damage Perspiration: 80 cycles ≥ 3/4; no damage
Flexing resistance (ISO 5402-1)	50,000 cycles, no cracks
Tear strength (ISO 3377-1)	≥ 20 N
Color fastness to water spotting (ISO 15700)	≥ 3; no swelling
Adhesion of finish (ISO 11644)	≥ 2 N/10 mm
Color fastness to artificial light (ISO 105-B02)	≥ 5 (96 h, 50°C)
Chemical compliance	REACH regulation CE 1907/2006 compliant
Storage & processing	10–12% humidity, max 80°C; avoid solvents; store dry at 15–25°C without heavy loads; test prototypes before production.
Finished product care	Store dry at room temperature; test cleaning products first; clean stains promptly by dabbing; air-dry and polish with soft cloth.
Notes	Values are average from standard production; specs may change without notice.